

| 产品大类 | 标准号 | 代表牌号 | 厚度 | 宽度 | 用途及特点 |
|-------|-----|-------|---------|----------|--|
| 淬火分配钢 | -- | QP980 | 0.8-2.0 | 900-1400 | <p>通过退火工艺使马氏体向残余奥氏体扩散，得到一定体积分数的亚稳定奥氏体，亚稳定奥氏体在变形过程中发生 TRIP 效应，从而得到良好的强度和塑性。第三代汽车用钢代表之一，用于汽车结构件、防撞件以及内部加强板。</p> <p>The annealing process to spread to the residual austenite martensite, metastable austenite to obtain a certain volume fraction, metastable austenite TRIP effect during the deformation process, so as to get a good strength and ductility. The third generation of automotive steel representative.</p> |